

NITROCELLULOSE SANDING SEALER

Product description	It is a nitrocellulose base air-drying sealer developed specially for wooden product before topcoating and easy sanding and excellent filling.	
Technical information	1) Surface dry	5-10 min at 25 ° c
	2) Hard dry	1-2 hr
	3) Solid content	40±1
	4) Specific gravity	1.003±0.05
	5) Viscosity at 25 ° c	3811 c.p
	6) Application method	Spray
	7) Cover rate	8-10 m ² /1kg
	8) Interval coat	60 min
Surface preparations	<ol style="list-style-type: none"> 1) Surface should be clean and free of dust, grease and oil. 2) Surface should be sanded using grit sand paper number 120 	

SimaFam Chemical Co.

Koushesh St - Lia Insurance Mini City - Qazvin - Iran

Tel: +9828 33454318

Email: info@simafam.com

Website: www.simafam.com